

## **Technical Data Sheet**

## Barite FPA BAR®-FS25

This Technical Data Sheet includes the values and data which are valid and trustable based on our current production process, but not legally binding. We hereby disclaim any liability arising from any damage, errors and omissions or consequential damage.

This Technical Data Sheet supersedes all previous versions. (December 2022)

Physical Properties		Chemical Analysis	
Whiteness (%)	80-82	BaO (%)	58.05
Brightness (%)	82	CaO (%)	2.37
Moisture	0.29	MgO (Max. %)	0.12
PH value (%)	8.20	Fe2O3 (%)	1.87
Hardness (MOHS)	4.5	Al2O3 (%)	0.08
General Data / Particle Size		SiO2(%)	2.10
Diameter at 10% (µ)	1.09	K2O(%)	0.00
Mean grain size D50 (μ)	4.07	S03(%)	30.4
Top – cut D98 (μ)	9.94	SrO(%)	2.11
Specific Gravity (g/ cm³)	4.3 - 4.4	Loss of Ignition (%)	2.98
Bulk Density (g/ cm³)	4.49	Applications;	Standard Packaging;
Apearance	Gray	Paint and Coating Paper & Printing Pharmaceutical Rubber Industry Medical, Etc.	25 Kg paper bag Bulk in Jumbo bag 25 Kg bags in Jumbo bag 25 Kg bags on pallet

Farayand Powder Alvan Co., is a leading manufacturer of micronized powders. We have more than 30 years of experience in producing different kind of products such as calcium carbonate, talc, barite, red and yellow iron oxides and industrial soot.

Head Office:

Ard Floor., No. 20, Baharan Alley, Shirazi Str., Tehran, Iran Tel: +98 (21) 88032858 Fax.: +98 (21) 88032688 Plant;

Industrial Zone, Dodehak Village, Delijan, Markazi Province, Iran Tel: +98 (86) 44260388 Fax.: +98 (86) 44260401

